

COMPARISON OF **PolyBak PB42** & **PolyBak PGB** TO Competitive Saturated Kraft Paper

| | Nominal Thickness In Inches | Machine Direction Tensile Strength (pounds per lineal inch) | Cross Direction Tensile Strength (pounds per lineal inch) | Water Absorption (% of water absorbed in a 2 hour soak.) <small>Tip: A higher rate of water absorption may mean more glue is required</small> | Contains Added Formaldehyde? | Greenguard Certified? | Will It Break If Bent 90 Degrees? | Easily Paintable? |
|--|-----------------------------|--|--|---|------------------------------|-----------------------|-----------------------------------|-------------------|
| PolyBak PB42 | 0.011 | 152 | 78 | 30% | NO | YES | NO | YES |
| PolyBak PGB | 0.011 | 128 | 49 | 56% | NO | YES | NO | YES |
| Competitive Saturated Kraft Paper | 0.020 | 100 | 70 | 71% | YES | NO | YES | NO |